




0058270AY

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com
www.mag-inc.com



High Flux Permeability (μ)	A_L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
125	103 $\pm$ 8%	N/A	N/A	N/A	Clear

Dimensions	Uncoated		Coated Limits			Packaging Bulk Pack 4 bags/box Box Qty= 10,000 pcs
	(mm)	(in)	(mm)	(in)		
OD (A)	6.60	0.260	7.06	0.278	max	
ID (B)	2.67	0.105	2.34	0.092	min	
HT (C)	4.78	0.188	5.23	0.206	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 100 kHz, 100mT max (mW/cm ³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _A (mm ²)	Cross Section A _e (mm ²)	Path Length L _e (mm)	Volume V _e (mm ³)	Weight (g)
1000	80%	50%	600	5.9	3.63	9.20	13.6	125	1.0000
	46.0	81.0							

Winding Information						Temperature Rating	
Winding Length Per Turn				Wound Coil Dimensions (mm)			Curie Temp: 500°C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	7.41	Coating Temp (Continuous up to): 130°C
					HT	6.11	
				Completely Full Window	Max OD	9.17	Notes: Parylene coated, color appears clear to milky white.
					Max HT	7.42	
0%	15.9	40%	17.0	Surface Area (mm²)			
20%	16.4	45%	17.2				
25%	16.6	50%	17.3				
30%	16.7	60%	17.7	Unwound Core		230	
35%	16.9	70%	18.0	40% Winding Factor		260	

Typical DC Bias Performance

