




0077312A7

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com
www.mag-inc.com




Kool Mμ Permeability (μ)	A _L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
26	19 ± 8%	XXXXXX	77312A7	N/A	Black

Dimensions	Uncoated		Coated Limits			Packaging Bulk Pack 4 bags/box Box Qty= 1000 pcs
	(mm)	(in)	(mm)	(in)		
OD (A)	22.86	0.900	23.62	0.930	max	
ID (B)	13.97	0.550	13.34	0.525	min	
HT (C)	7.62	0.300	8.38	0.330	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 100 kHz, 100mT max(mW/cm ³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _A (mm ²)	Cross Section A _e (mm ²)	Path Length L _e (mm)	Volume V _e (mm ³)	Weight (g)
900	80%	50%	>3000	39.0	139	31.7	56.7	1,800	10.32
	95.0	205							

Winding Information						Temperature Rating		
Winding Length Per Turn				Wound Coil Dimensions (mm)			Curie Temp: 500°C	
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	25.7	Coating Temp (Continuous up to): 200°C	
					HT	12.4		
				Completely Full Window	Max OD	32.6		Notes:
					Max HT	19.8		
0%	27.0	40%	33.9	Surface Area (mm²)				
20%	30.5	45%	34.9					
25%	31.3	50%	35.9					
30%	32.0	60%	38.0	Unwound Core		1,600		
35%	33.1	70%	40.4	40% Winding Factor		2,400		

Typical DC Bias Performance



Revision 10/6/2021