FERROXCUBE

DATA SHEET

P18/11/I P cores and accessories

Supersedes data of September 2004

2008 Sep 01




P cores and accessories

CORE SETS

Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
$\Sigma(I/A)$	core factor (C1)	0.560	mm ⁻¹
V _e	effective volume	1270	mm ³
l _e	effective length	26.7	mm
A _e	effective area	47.5	mm ²
A _{min}	minimum area	37.5	mm ²
m	mass of set	≈ 7	g



Core sets for general purpose transformers and power applications

Clamping force for A_L measurements, 30 ± 10 N.

GRADE	A _L (nH)	$\mu_{\mathbf{e}}$	AIR GAP (μm)	TYPE NUMBER
3C81	160 ±3%	≈ 72	≈ 450	P18/11/I-3C81-A160
	250 ±3%	≈ 112	≈ 260	P18/11/I-3C81-A250
	315 ±3%	≈ 141	≈ 200	P18/11/I-3C81-A315
	400 ±3%	≈ 179	≈ 150	P18/11/I-3C81-A400
	630 ±5%	≈ 282	≈ 90	P18/11/I-3C81-A630
	4200 ±25%	≈ 1880	≈ 0	P18/11/I-3C81
3C91 des	4200 ±25%	≈ 1880	≈ 0	P18/11/I-3C91
3F3	160 ±3%	≈ 72	≈ 450	P18/11/I-3F3-A160
	250 ±3%	≈ 112	≈ 260	P18/11/I-3F3-A250
	315 ±3%	≈ 141	≈ 200	P18/11/I-3F3-A315
	400 ±3%	≈ 179	≈ 150	P18/11/I-3F3-A400
	630 ±5%	≈ 282	≈ 90	P18/11/I-3F3-A630
	3110 ±25%	≈ 1390	≈ 0	P18/11/I-3F3

2008 Sep 01 976

P cores and accessories

P18/11/I

Properties of core sets under power conditions

	B (mT) at	CORE LOSS (W) at			
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 100 °C	f = 400 kHz; B = 50 mT; T = 100 °C
3C81	≥320	≤ 0.3	_	_	_
3C91	≥315	_	≤ 0.08 ⁽¹⁾	≤ 0.5 ⁽¹⁾	-
3F3	≥315	_	≤ 0.14	_	≤ 0.24

Note

1. Measured at 60 °C.

BOBBINS AND ACCESSORIES

Coil formers, winding data and mounting parts are equal to those of "P18/11", but "area product" is different.

Winding data and area product (for P18/11/I) for CP-P18/11 coil former

NUMBER OF SECTIONS	WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm ⁴)	TYPE NUMBER
1	17.1	5.7	36.6	812	CP-P18/11-1S
2	2 × 7.95	2 × 2.65	36.6	2 x 378	CP-P18/11-2S
3	3×4.95	3×1.6	36.6	3 x 235	CP-P18/11-3S

Winding data and area product (for P18/11/I) for 6-pins P18/11 coil former for PCB mounting

NUMBER OF SECTIONS	MINIMUM WINDING AREA (mm²)	NOMINAL WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	LENGTH OF PINS (mm)	AREA PRODUCT Ae x Aw (mm ⁴)	TYPE NUMBER
1	16.8	6.0	36.7	4.4	798	CPV-P18/11-1S-6PD
1	16.8	6.0	36.7	6.8	798	CPV-P18/11-1S-6PDL
2	2×7.61	2×2.8	36.7	4.4	2 x 361	CPV-P18/11-2S-6PD
2	2×7.61	2×2.8	36.7	6.8	2 x 361	CPV-P18/11-2S-6PDL
3	3 × 4.58	3 × 1.7	36.7	4.4	3 x 218	CPV-P18/11-3S-6PD
3	3 × 4.58	3 × 1.7	36.7	6.8	3 x 218	CPV-P18/11-3S-6PDL

2008 Sep 01 977

P cores and accessories

P18/11/I

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

2008 Sep 01 978